


Emhart Glass 1380-30 Material Technical Data Sheet

Mix ID:	1380-30			
Mix Name:				
Type:	Insulation			
Application:	Celatom MN-41 is a natural diatomaceous earth product. Used as a bulking aid, anticaking agent, catalyst support, or general filler. Amorphous silica, inert in most acidic solutions.			
Typicals:	Mesh:	5.0% on -325	Chemistry:	Wt. %
				
	Dry Loose Density:	12 lb/ft ³	Al ₂ O ₃	5.6
			SiO ₂	83.7
	Specific Gravity:	1.98 – 2.02 g/cc	ZrO ₂	N/A
			Fe ₂ O ₃	2.3
	MOR:	N/A	Na ₂ O-K ₂ O	N/A
			CaO	.4
	Maximum Use Temperature:	N/A	MgO	.3
			Other	1.9
Melting Point	N/A	L.O.I.	5.3	

All data is subject to reasonable deviations and not to be used for specification purposes.