


Emhart Glass 386 - Material Technical Data Sheet

Mix ID:	386			
Mix Name:	211-HH			
Type:	Hand Molded			
Application:	Ring Clay			
Typicals:	Porosity:		Chemistry:	Wt.%
(Fired to 2100° F)				
 REFRACTORY PRODUCTS	Density:		Al₂O₃	31.6
			SiO₂	61.1
	Apparent Specific Gravity:		Fe₂O₃	.9
			NaO	N/A
	MOR:		CaO	.1
			MgO	.2
	PCE:		TiO₂	1.4
			L.O.I.	4.0
	Linear Thermal Expansion: (200°C – 1000°C)		Other	.7

All data is subject to reasonable deviations and not to be used for specification purposes.